

**Electronic structure of BaNi<sub>2</sub>As<sub>2</sub>**Bo Zhou,<sup>1</sup> Min Xu,<sup>1</sup> Yan Zhang,<sup>1</sup> Gang Xu,<sup>2</sup> Cheng He,<sup>1</sup> L. X. Yang,<sup>1</sup> Fei Chen,<sup>1</sup> B. P. Xie,<sup>1</sup> Xiao-Yu Cui,<sup>3</sup> Masashi Arita,<sup>4</sup> Kenya Shimada,<sup>4</sup> Hirofumi Namatame,<sup>4</sup> Masaki Taniguchi,<sup>4</sup> X. Dai,<sup>2</sup> and D. L. Feng<sup>1,\*</sup><sup>1</sup>*Department of Physics, State Key Laboratory of Surface Physics, Key Laboratory of Micro and Nano Photonic Structures (MOE), Fudan University, Shanghai 200433, People's Republic of China*<sup>2</sup>*Beijing National Laboratory for Condensed Matter Physics, Institute of Physics, Chinese Academy of Sciences, Beijing 100190, People's Republic of China*<sup>3</sup>*Swiss Light Source, Paul-Scherrer Institut, CH-5232 Villigen, Switzerland*<sup>4</sup>*Hiroshima Synchrotron Radiation Center and Graduate School of Science, Hiroshima University, Hiroshima 739-8526, Japan*

(Received 9 October 2010; published 13 January 2011)

BaNi<sub>2</sub>As<sub>2</sub>, with a first-order phase transition around 131 K, is studied by the angle-resolved photoemission spectroscopy. The measured electronic structure is compared to the local-density approximation calculations, revealing similar large electronlike bands around  $\bar{M}$  and differences along  $\bar{\Gamma}$ - $\bar{X}$ . We further show that the electronic structure of BaNi<sub>2</sub>As<sub>2</sub> is distinct from that of the sibling iron pnictides. Particularly, there is no signature of band folding, indicating no collinear spin-density-wave-related magnetic ordering. Moreover, across the strong first-order phase transition, the band shift exhibits a hysteresis, which is directly related to the significant lattice distortion in BaNi<sub>2</sub>As<sub>2</sub>.

DOI: [10.1103/PhysRevB.83.035110](https://doi.org/10.1103/PhysRevB.83.035110)

PACS number(s): 79.60.-i, 74.25.Jb, 71.20.-b, 74.70.-b

**I. INTRODUCTION**

The discovery of iron-based high-temperature superconductors has ignited intensive studies.<sup>1-9</sup> The superconducting transition temperature ( $T_c$ ) has risen up to 56 K in RFeAsO<sub>1-x</sub>F<sub>x</sub> ( $R = \text{Sm, Nd, Pr, } \dots$ ).<sup>3-8</sup> On the other hand, the sibling Ni-based compounds only possess relatively low  $T_c$ , i.e., LaONiP ( $T_c = 3$  K),<sup>10</sup> LaONiAs ( $T_c = 2.75$  K),<sup>11</sup> BaNi<sub>2</sub>P<sub>2</sub> ( $T_c = 2.4$  K),<sup>12</sup> BaNi<sub>2</sub>As<sub>2</sub> ( $T_c = 0.7$  K),<sup>13</sup> and SrNi<sub>2</sub>As<sub>2</sub> ( $T_c = 0.62$  K).<sup>14</sup> It is intriguing to understand why  $T_c$  is low in the Ni-based compounds, which may facilitate understanding the high  $T_c$  in iron-based ones.

BaFe<sub>2</sub>As<sub>2</sub>, a typical parent compound of an iron-based superconductor with the ThCr<sub>2</sub>Si<sub>2</sub> structure, exhibits a structural transition from tetragonal to orthorhombic, concomitant with a spin-density-wave (SDW) transition at 140 K.<sup>15</sup> The structural transition was suggested to be driven by the magnetic degree of freedom.<sup>16-21</sup> BaNi<sub>2</sub>As<sub>2</sub>, with the same structure, displays a structural transition around 131 K, however, from a tetragonal phase to a lower symmetry triclinic phase.<sup>22</sup> No evidence of SDW is reported in BaNi<sub>2</sub>As<sub>2</sub> so far. On the other hand, it was pointed out that the transition in BaNi<sub>2</sub>As<sub>2</sub> is a first-order one, while that is more second orderlike in BaFe<sub>2</sub>As<sub>2</sub>.<sup>22</sup> Moreover, the  $c$ -axis resistivity drops by 2 orders of magnitude, and a thermal hysteresis of in-plane resistivity is present at the transition of BaNi<sub>2</sub>As<sub>2</sub>.<sup>13,22</sup> Although there are intriguing resemblances as well as differences between BaFe<sub>2</sub>As<sub>2</sub> and BaNi<sub>2</sub>As<sub>2</sub>, the electronic structure of the latter is still not exposed.

Here, we report the angle-resolved photoemission spectroscopy (ARPES) study of the electronic structure of BaNi<sub>2</sub>As<sub>2</sub>. Our data are compared to the band-structure calculation of BaNi<sub>2</sub>As<sub>2</sub> and the results of iron pnictides reported before, revealing their similarities and differences. Particularly, no band folding is found in the electronic structure of BaNi<sub>2</sub>As<sub>2</sub>, confirming that there is no collinear SDW type of magnetic ordering. Because of the intimate relation

between superconductivity and magnetism,<sup>23-26</sup> the absence of magnetic ordering is possibly related to the low  $T_c$  of BaNi<sub>2</sub>As<sub>2</sub>. Furthermore, a hysteresis is observed for the band shift, resembling the hysteresis in the resistivity data. The band shift can be accounted for by the significant lattice distortion in BaNi<sub>2</sub>As<sub>2</sub>, in contrast to iron pnictides, where the band shift is largely caused by the magnetic ordering.

**II. EXPERIMENTAL**

BaNi<sub>2</sub>As<sub>2</sub> single crystals were synthesized by the self-flux method, and a similar synthesis procedure has been described in Ref. 22. Its stoichiometry was confirmed by energy dispersive x-ray analysis. ARPES measurements were performed (1) with circularly polarized synchrotron light and randomly polarized 8.4-eV photons from a xenon discharge lamp at Beamline 9 of the Hiroshima synchrotron radiation center (HSRC), (2) with linearly polarized synchrotron light at the surface and interface spectroscopy beamline of the Swiss Light Source (SLS), and (3) with randomly polarized 21.2-eV photons from a helium discharge lamp. Scienta R4000 electron analyzers were equipped in all setups. The typical energy resolution is 15 meV, and angular resolution is 0.3°. The samples were cleaved *in situ* and measured in ultrahigh vacuum better than  $5 \times 10^{-11}$  mbar. The high-quality sample surface was confirmed by the clear pattern of low-energy electron diffraction, where no sign of surface reconstruction was observed (Fig. 1).

**III. EXPERIMENTAL RESULTS**

Figures 2(a) and 2(c) show the Fermi surface maps measured with circularly polarized 22.5-eV photons in the tetragonal and triclinic phases, respectively. There are four patches near the  $\bar{\Gamma}$  point as indicated by the arrows and two electron pockets around the  $\bar{M}$  point. Sixteen cuts from  $\bar{\Gamma}$  to  $\bar{M}$  are presented in Fig. 2(b) to illustrate the electronic structure




FIG. 1. The low-energy electron diffraction pattern of  $\text{BaNi}_2\text{As}_2$  in the triclinic phase taken with 100-eV incident electrons.

evolution in the tetragonal phase, and the corresponding data in the triclinic phase are shown in Fig. 2(d). In the tetragonal phase, the parabolic-shaped band in cuts 1 and 2 around  $\bar{\Gamma}$  is referred to as  $\alpha$ . The  $\alpha$  band appears to be  $M$  shaped in cuts 3 and 4. From cut 1 to cut 4, the parabolic part shrinks continuously, and eventually, only the inverted parabolic part is observed in cuts 5–7. The evolution of the electronlike bands around  $\bar{M}$  are shown in cuts 8–16, many of which are complex due to the rapid change of dispersions. Nonetheless, two bands ( $\beta$  and  $\gamma$ ) can be resolved as indicated by the dashed curves in cut 16 and will be further elaborated on in Fig. 4. The data in the triclinic phase [Fig. 2(d)] are generally similar to those in the tetragonal phase. Nonetheless, we note that  $\alpha$  already shows some bending near the Fermi energy ( $E_F$ ) in the tetragonal phase as indicated by the arrows on the data taken along cuts 1 and 2. On the other hand,  $\alpha$  just passes through  $E_F$  without bending in the triclinic phase. Moreover, the band top of  $\alpha$  is below  $E_F$  in cuts 6 and 7 of Fig. 2(b) as indicated by the arrows but barely touches  $E_F$  in Fig. 2(d), where cuts 6 and 7 pass through one of the four patches around  $\bar{\Gamma}$ . Therefore, the four spectral weight patches around  $\bar{\Gamma}$  [as marked by four arrows in Fig. 2(a)] are due to the residual spectral weight of the  $\alpha$  band in the tetragonal phase. However, the  $\alpha$  bands shift up, and they evolve into small holelike Fermi surfaces in the triclinic phase. This will be further illustrated in Fig. 3. Of note, from this complete set of data, we do not observe any sign of band folding or splitting like that in the iron pnictides.<sup>27–31</sup>

To further illustrate the electronic structure of  $\text{BaNi}_2\text{As}_2$ , Figs. 3(a)–3(e) present photoemission intensities along five cuts parallel to the  $\bar{\Gamma}$ - $\bar{X}$  direction in the triclinic phase. The  $M$ -shaped feature originated from  $\alpha$  simply moves toward  $E_F$  from cut 1 to cut 5, touching  $E_F$  at cuts 4 and 5, which confirms that the four small Fermi surfaces around  $\bar{\Gamma}$  are holelike. Note that the downward part of  $\alpha$  [indicated by the arrow in Fig. 3(e)] is clearly resolved here, while it is barely observed in the same momentum region when the cuts are along the  $\bar{\Gamma}$ - $\bar{M}$  direction, as shown in cuts 1 and 2 of Figs. 2(b) and 2(d). It highlights the matrix element effects since the  $3d$  orbitals have specific orientations. Figure 3(f) shows the photoemission intensity along  $\bar{\Gamma}$ - $\bar{X}$ , taken with randomly polarized 21.2-eV photons

from a helium lamp in the triclinic phase. The determined band structure is traced by dashed curves, where the broad spectral weight around  $\bar{X}$  is attributed to an electronlike band  $\delta$ , which is further shown by markers in the corresponding MDCs [Fig. 3(g)]. Therefore, there is an electron Fermi pocket around  $\bar{X}$ .

Similar to iron pnictides, the bands near  $E_F$  are quite complicated and mainly contributed to by the Ni  $3d$  electrons in  $\text{BaNi}_2\text{As}_2$ . To resolve the complex bands around  $\bar{M}$ , we utilize the linearly polarized light, which could only detect bands with certain symmetry so that the measured partial electronic structure helps to reduce the complexity in analysis.<sup>32</sup> Figure 4 presents data along  $\bar{\Gamma}$ - $\bar{M}$ , taken with linearly polarized 100-eV photons in the SLS in the triclinic phase. Two polarization geometries ( $s$  and  $p$ ) are illustrated in Fig. 4(a). In the  $s$ -polarization geometry, we resolve two bands, whose dispersions are depicted by dashed curves in the photoemission intensity plot [Fig. 4(b)]. While in the  $p$ -polarization geometry, one intense parabolic electronlike band around  $\bar{M}$  is resolved with the band bottom at about  $-0.57$  eV. The dispersions in both geometries are marked in the corresponding MDCs [Fig. 4(d)]. The asymmetry of the dispersion indicated by triangles may be due to the slight sample misalignment. The image contrast in the dashed-dotted region in Fig. 4(c) is adjusted to highlight the  $\alpha$  feature. The observed  $\alpha$  feature is consistent with the data in Figs. 2 and 3. By comparing with the Fermi crossings observed in cuts 1 and 16 of Fig. 2(d), we attribute the three bands to  $\alpha$ ,  $\beta$ , and  $\gamma$  as shown in Fig. 4(d), where  $\beta$  and  $\gamma$  are two electronlike bands around  $\bar{M}$ . Moreover, since the experimental setup under the  $s$ - ( $p$ -) polarization geometry detects states with odd (even) symmetry with respect to the mirror plane; the  $\beta$  band is mainly of odd symmetry while  $\gamma$  is of even symmetry. We note that  $\alpha$  is observed in both geometries [Figs. 4(b) and 4(c)], suggesting that the  $\alpha$  band has mixed symmetries.

To study the first-order transition of  $\text{BaNi}_2\text{As}_2$ , the temperature dependence is presented in Fig. 5. The photoemission intensity plots along  $\bar{\Gamma}$ - $\bar{X}$  are shown in Figs. 5(b) and 5(c) for the tetragonal and the triclinic phases, respectively. The corresponding EDCs at  $k_{\parallel} = 0$  are stacked in Fig. 5(d). Interestingly, the band bottom of the  $M$ -shaped feature is moved from  $-200$  meV in the tetragonal phase to  $-170$  meV in the triclinic phase. In other words, the  $M$ -shaped band moves toward  $E_F$ , and its electronic energy is raised. However, another feature at higher binding energies shifts away from  $E_F$ . Its band top is moved from  $-350$  meV at 145 K to  $-390$  meV at 12 K, which partially saves the electronic energy. Since the resistivity shows a hysteresis loop,<sup>13</sup> it is intriguing to investigate whether a similar hysteresis could be observed for the electronic structure. Data in Figs. 5(e) and 5(f) are taken with randomly polarized 8.4-eV photons from a xenon discharge lamp in a cooling-warming-cooling cycle. The EDCs at  $k_{\parallel} = 0$  across the transition are stacked in Fig. 5(e), where the peak positions are indicated by short bars. The temperature dependence of peak positions is summarized in Fig. 5(f), showing a clear hysteresis with the band shift as much as 25 meV. Such an electronic structure demonstration of a hysteresis of 3 K is so far the most obvious. A hysteresis in the electronic structure has been observed in




FIG. 2. (Color online) Photoemission data of BaNi<sub>2</sub>As<sub>2</sub>. (a) Photoemission intensity map at the Fermi energy ( $E_F$ ) measured at 150 K in the tetragonal phase. For the convenience of data presentation, the two-dimensional (2D) Brillouin zone is referred to hereafter, which is the projection of three-dimensional (3D) Brillouin zone. (b) Photoemission intensity plots of cuts 1–16 as indicated in panel (a). (c) and (d) are the same as panels (a) and (b) but for data measured at 13 K in the triclinic phase. Band dispersions are indicated by the dashed curves. Data were taken in HSRC with circularly polarized 22.5-eV photons. Labels are explained in the text.

FeTe but with a loop width of only 0.5 K.<sup>33</sup> Our observation here is consistent with the bulk transport properties, which indicates that the measured electronic structure reflects the bulk properties.

#### IV. BAND-STRUCTURE CALCULATIONS

The measured band structure and Fermi surface are summarized in Figs. 6(a), 6(d), and 6(e). For comparison, local-density

approximation calculations, which have been reported before in Ref. 34 are reproduced in Figs. 6(b), 6(f), and 6(g). The notations for bands near  $E_F$  are labeled in Figs. 6(a) and 6(b). Qualitatively, although not all calculated bands were observed, the main features of the experiments were captured by the calculation, such as the dispersion nature of the bands. The  $\alpha$ ,  $\beta$ , and  $\gamma$  bands of the experimental results in the  $\bar{\Gamma}$ - $\bar{M}$  direction are similar to the numerical results in the Z-A direction. As shown in Fig. 6(c), the measured  $\alpha$  band






FIG. 3. (Color online) Photoemission data along several cuts parallel to  $\bar{\Gamma}$ - $\bar{X}$  in the triclinic phase. (a)–(e) Photoemission intensity plots of cuts 1–5 as indicated in panel (g), taken in the HSRC with circularly polarized 21.2-eV photons at 20 K. (f) Photoemission intensity plot of cut 6 as indicated in panel (g), taken with randomly polarized 21.2-eV photons from a helium lamp at 25 K. (g) The momentum distribution curves (MDCs) corresponding to panel (f). (h) Cuts 1–6 are indicated in the projected 2D Brillouin zone. The dashed curves and markers trace the band dispersions.

along  $\bar{\Gamma}$ - $\bar{M}$  matches the calculation well after the calculated bands are renormalized by a factor of 1.66 and shifted down by 0.08 eV. This renormalization factor is consistent with the results of optical measurements.<sup>34</sup> Although not all bands could match, it may suggest that the correlation in  $\text{BaNi}_2\text{As}_2$  is weaker than that in iron pnictides.<sup>27,35</sup> Along  $\bar{\Gamma}$ - $\bar{X}$ , the observed  $\alpha$  and  $\delta$  bands partially resemble the calculated dispersions along both  $Z$ - $R$  and  $\Gamma$ - $X$ , as highlighted by the shaded regions [Fig. 6(b)], but the energy positions do not match. Our data along this direction might correspond to a  $k_z$  between  $\Gamma$  and  $Z$ .

As expected from the differences in the experimentally determined and calculated band structures, the Fermi-surface topologies are quite different in both the experiments and the calculations. In our data [Figs. 6(d) and 6(e)], we observe four small Fermi pockets around  $\bar{\Gamma}$  only in the triclinic phase. Around  $\bar{M}$ , two electronlike Fermi pockets are resolved in both phases. Around  $\bar{X}$ , the observed Fermi crossings are from an electronlike pocket. As a comparison, in the calculated Fermi surface of high- $T$  tetragonal phase [Figs. 6(f)], there are two large warped cylinders of electron pockets around the zone corner, a pocket interconnected from the zone center to a large deformed cylinder around the zone corner, a 3D electron pocket around  $Z$ , and 3D pockets located between  $X$  and  $R$ . In the low- $T$  triclinic phase [Figs. 6(g)], 3D pockets




FIG. 4. (Color online) Photoemission data along  $\bar{\Gamma}$ - $\bar{M}$  measured at 10 K in the triclinic phase with 100-eV linearly polarized light at the SLS. (a) Experimental setup for the  $s$ - and  $p$ -polarization geometries and the indication of the  $\bar{\Gamma}$ - $\bar{M}$  cut in the projected 2D Brillouin zone. (b) and (c) Photoemission intensity plots measured in the  $s$ - and  $p$ -polarization geometries, respectively. The image contrast in the rectangular region as enclosed by dashed-dotted lines in panel (c) is adjusted to reveal the bands in this region. (d) Stack of MDCs in the  $s$ - and  $p$ -polarization geometries. Each MDC is normalized by its integrated weight. Dashed curves and markers trace the band dispersions. Labels are explained in the text.

around  $Z$  and between  $X$  and  $R$  are gapped out. The large electron Fermi pockets around  $\bar{M}$  observed in our data are generally consistent with that in the calculation, which is a direct consequence of two more electrons from Ni than Fe. Note that the  $k_z$  dispersion is significant in the calculation. However, we have measured with four different photon energies, including the more bulk-sensitive 8.4-eV photons, and no obvious differences in dispersion have been observed. Therefore, the  $k_z$  dispersions in  $\text{BaNi}_2\text{As}_2$  may be weaker than calculated.

For a multiband and multiorbital superconductor, it is crucial to understand the orbital characters of the band structure. Because of the symmetry of 3d orbitals with respect to the mirror plane, the  $s$ -polarization geometry in photoemission can only detect the  $d_{xy}$  and  $d_{yz}$  orbitals, while the  $p$ -polarization geometry can only detect the  $d_{x^2-y^2}$ ,  $d_{z^2}$ , and  $d_{xz}$  orbitals [Fig. 7(a)].<sup>32</sup> The contributions of the five 3d orbitals to the calculated band structure are presented in Figs. 7(b)–7(f), which, therefore, can be compared to our polarization-dependent data. Along  $Z$ - $A$ , the  $\alpha$  band mainly consists of the odd  $d_{xy}$  orbital and some contributions of odd  $d_{yz}$  and even  $d_{xz}$ , thus, can be observed in both the  $s$ - and  $p$ -polarization geometries; while the  $\gamma$  band consists




FIG. 5. (Color online) Temperature dependence of photoemission data. (a) Indication of the cut by the thick line in the projected 2D Brillouin zone. (b) and (c) Photoemission intensity plots along the cut shown in panel a measured at 145 and 12 K, respectively. (d) Comparison of energy-distribution curves (EDCs) at  $k_{\parallel} = 0$  for data shown in panels (b) and (c). Data were taken in HSRC with circularly polarized 22.5-eV photons for panels (b)–(d). (e) EDCs at  $k_{\parallel} = 0$  for a cooling-warming-cooling cycle, measured with randomly polarized 8.4-eV photons from a xenon discharge lamp. The short bars indicate the peak positions. (f) Summary of peak positions obtained from panel (e), which exhibits a hysteresis.

of the even  $d_{x^2-y^2}$  and  $d_{z^2}$  orbitals, thus, can only be observed in the  $p$ -polarization geometry. They are in good agreement with our observation. The  $\beta$  band consists of the odd  $d_{xy}$ ,  $d_{yz}$  and even  $d_{xz}$  orbitals in the calculation and, thus, should be observed in both the  $s$ - and  $p$ -polarization geometries. However,  $\beta$  is mainly detected in the  $s$ -polarization geometry, possibly, because, in the  $p$ -polarization geometry, it is buried in the intense peak of  $\gamma$ . The consistency between our data and the calculated orbital characters confirms that our data along  $\bar{\Gamma}$ - $\bar{M}$  match the band structure calculation along  $Z$ - $A$ .

## V. DISCUSSIONS

It was observed in the optical data that the phase transition leads to a reduction of conducting carriers, consistent with the removal of small Fermi surfaces shown by the calculation.<sup>34</sup> However, we do not observe such behavior by ARPES. On the

contrary, instead of the disappearance of small Fermi surfaces in the triclinic phase, we observe that bands shift up in energy, leading to additional four Fermi surfaces. The inconsistency between the optical data and our photoemission data suggests that the changes in optical data across the phase transition are possibly an integrated effect of band-structure reorganization over the entire Brillouin zone, instead of the disappearance of certain Fermi-surface sheets; but it is also possible that only limited  $k$  space has been probed in the current photoemission study.

As a sibling compound of iron pnictides, BaNi<sub>2</sub>As<sub>2</sub> exhibits quite different properties and electronic structure. The parent compounds of iron pnictides show a second-order-like transition that is the SDW transition concomitant with a structural transition. However, BaNi<sub>2</sub>As<sub>2</sub> shows a strong first-order-like structural transition, without magnetic ordering reported to date. From the aspect of electronic structure, iron pnictides possess several hole pockets around  $\bar{\Gamma}$  and several electron pockets around  $\bar{M}$  but have no pockets around  $\bar{X}$ , while the band structure of BaNi<sub>2</sub>As<sub>2</sub> is dramatically different from that of the iron pnictides. Moreover, no signature of folding could be found in our data, confirming that no collinear magnetic ordering exists in BaNi<sub>2</sub>As<sub>2</sub>. Because of the intimate relation between the magnetism and superconductivity,<sup>23–26</sup> the absence of magnetic ordering might be related to the low  $T_c$  in BaNi<sub>2</sub>As<sub>2</sub>.

Across the structural transition in BaNi<sub>2</sub>As<sub>2</sub>, the Ni-Ni distance changes from 2.93 Å<sup>-1</sup> to 2.8 Å<sup>-1</sup> (or 3.1 Å<sup>-1</sup>), corresponding to a lattice distortion as much as  $\sim 5\%$  on average.<sup>22</sup> A rough estimation can be made for the hopping parameter  $t_{dd}$  between certain  $d$ - $d$  orbitals after the lattice distortion according to Ref. 36,

$$t_{dd} = t_{dd}^0(1 + \delta)^{-7/2} \approx t_{dd}^0 \left(1 - \frac{7}{2}\delta\right),$$

$$\implies \Delta t = t_{dd} - t_{dd}^0 = -\frac{7}{2}\delta t_{dd}^0,$$

where  $\delta$  is the relative lattice distortion;  $t_{dd}^0$  is the hopping parameter before the distortion;  $\Delta t$  is the induced hopping parameter change. Therefore, the 5% lattice distortion would cause  $\sim 17.5\%$  of change to  $t_{dd}^0$ . Since the measured bandwidth of  $\alpha$  is at least 200 meV, the induced band shift would be larger than 35 meV, more than enough to account for the measured band shift of 25 meV. Note that the differences between the calculated band structures of tetragonal and triclinic phases in Fig. 6(f) are solely induced by considering the different lattice parameters. For instance, the band along  $Z$ - $R$  near  $E_F$  has a shift of 25% of the bandwidth, generally consistent with our observation. Therefore, our BaNi<sub>2</sub>As<sub>2</sub> data provide a prototypical experimental showcase of band shift due to significant lattice distortion. As a comparison, the lattice distortion in NaFeAs is 0.36%, which would induce only 1 meV of band shift, much smaller than the observed 16 meV by ARPES.<sup>19</sup> Similar results can be found in other iron pnictides.<sup>27–31</sup> The minor lattice distortion cannot account for the large band shift observed in iron pnictides; therefore, it has been concluded that the only promising explanation left is that the band shift is related to the magnetism.<sup>19,37</sup>




FIG. 6. (Color online) (a) Band structure along  $\bar{X}\text{-}\bar{\Gamma}\text{-}\bar{M}$  in the triclinic phase summarized from Figs. 3 and 4. (b) Calculated band structures in the tetragonal (dashed curves) and triclinic (solid curves) phases.<sup>34</sup> (c) Experimental band structure from panel (a) (dashed curves) overlaid by the calculated band structure (solid curves) in the triclinic phase. The energy scale of the calculated band structure at the right side is 1.66 times the energy scale of the experimental one on the left side. The summary of experimental Fermi contours (d) in the tetragonal phase and (e) in the triclinic phase, respectively. The small circles indicate the small Fermi surfaces around  $\bar{\Gamma}$ , and the dashed circles indicate the Fermi surface around  $\bar{X}$ . The sketches are depicted, in part, for the projected 2D Brillouin zone. (f) and (g) The calculated 3D Fermi surfaces in the tetragonal and triclinic phases, respectively.<sup>34</sup> (h) The 3D tetragonal Brillouin zone (thick lines) with notations for high-symmetry points. Labels are explained in the text.




FIG. 7. (Color online) (a) Illustration of the in-plane spatial symmetry of 3d orbitals. (b)–(f) Contributions of the  $d_{xy}$ ,  $d_{yz}$ ,  $d_{x^2-y^2}$ ,  $d_{z^2}$ , and  $d_{xz}$  orbitals to the calculated band structure of  $\text{BaNi}_2\text{As}_2$ , respectively. The contribution is represented by both the size of the symbols and the color scale.

## VI. CONCLUSIONS

To summarize, we report the first electronic structure study of BaNi<sub>2</sub>As<sub>2</sub> by ARPES. In comparison with the band calculation of BaNi<sub>2</sub>As<sub>2</sub> and reports of iron pnictides, we conclude several points as follows:

(i) We observe four small Fermi pockets around  $\bar{\Gamma}$  only in the triclinic phase, an electronlike pocket around  $\bar{X}$  and two electronlike pockets around  $\bar{M}$  in both tetragonal and triclinic phases. The main features of the measured band structure along  $\bar{\Gamma}$ - $\bar{M}$  is qualitatively captured by the band calculations, however, differences exist along  $\bar{\Gamma}$ - $\bar{X}$ . The electronic structure of BaNi<sub>2</sub>As<sub>2</sub> is also distinct from that of iron pnictides. Moreover, the correlation effects in BaNi<sub>2</sub>As<sub>2</sub> seem to be weaker than that in iron pnictides, as the band renormalization factor is smaller for BaNi<sub>2</sub>As<sub>2</sub>.

(ii) Unlike iron pnictides, we do not observe any sign of band folding in BaNi<sub>2</sub>As<sub>2</sub>, confirming no collinear SDW-related magnetic ordering. Since the magnetism intimately relates to the superconductivity, possibly this is why the  $T_c$  is much lower in BaNi<sub>2</sub>As<sub>2</sub> than in iron pnictides.

(iii) The SDW-structural transition in iron pnictides is second orderlike, while the structural transition in BaNi<sub>2</sub>As<sub>2</sub> is first orderlike, and a thermal hysteresis is observed for its band shift.

(iv) The band shift in BaNi<sub>2</sub>As<sub>2</sub> is caused by the significant lattice distortion. On the other hand, the band shifts in the iron pnictides cannot be accounted for by the minor lattice distortion there but are related to the magnetic ordering.

## ACKNOWLEDGMENTS

Part of this work was performed at the Surface and Interface Spectroscopy beamline, SLS, Paul Scherrer Institute, Villigen, Switzerland. We thank C. Hess and F. Dubi for technical support. This work was supported by the National Natural Science Foundation of China, Ministry of Education, Ministry of Science and Technology (National Basic Research Program under Grants No. 2006CB921300 and No. 2006CB601002), Science and Technology Commission of Shanghai Municipality of China.

\*dlfeng@fudan.edu.cn

<sup>1</sup>Y. Kamihara, T. Watanabe, M. Hirano, and H. Hosono, *J. Am. Chem. Soc.* **130**, 3296 (2008).

<sup>2</sup>X. H. Chen, T. Wu, G. Wu, R. H. Liu, H. Chen, and D. F. Fang, *Nature (London)* **453**, 761 (2008).

<sup>3</sup>Z. A. Ren, W. Lu, J. Yang, W. Yi, X.-L. Shen, Z. Cai, G.-C. Che, X.-L. Dong, L.-L. Sun, F. Zhou, and Z.-X. Zhao, *Chin. Phys. Lett.* **25**, 2215 (2008).

<sup>4</sup>R. H. Liu, G. Wu, T. Wu, D. F. Fang, H. Chen, S. Y. Li, K. Liu, Y. L. Xie, X. F. Wang, R. L. Yang, L. Ding, C. He, D. L. Feng, and X. H. Chen, *Phys. Rev. Lett.* **101**, 087001 (2008).

<sup>5</sup>Chunlei Wang, Zhaoshun Gao, Lei Wang, Yanpeng Qi, Dongliang Wang, Chao Yao, Zhiyu Zhang, and Yanwei Ma, *Supercond. Sci. Technol.* **23**, 055002 (2010).

<sup>6</sup>Zhi-An Ren, Jie Yang, Wei Lu, Wei Yi, Xiao-Li Shen, Zheng-Cai Li, Guang-Can Che, Xiao-Li Dong, Li-Ling Sun, Fang Zhou, and Zhong-Xian Zhao, *Europhys. Lett.* **82**, 57002 (2008).

<sup>7</sup>A. Kursumovic, J. H. Durrell, S. K. Chen, and J. L. MacManus-Driscoll, *Supercond. Sci. Technol.* **23**, 025022 (2010).

<sup>8</sup>Z. A. Ren, J. Yang, W. Lu, W. Yi, G. C. Che, X. L. Dong, L. L. Sun, and Z. X. Zhao, *Mater. Res. Innovations* **12**, 105 (2008).

<sup>9</sup>Min Xu, Fei Chen, Cheng He, Hong-Wei Ou, Jia-Feng Zhao and Dong-Lai Feng, *Chem. Mater.* **20**, 7201 (2008).

<sup>10</sup>Takumi Watanabe, Hiroshi Yanagi, Toshio Kamiya, Yoichi Kamihara, Hidenori Hiramatsu, Masahiro Hirano, and Hideo Hosono, *Inorg. Chem.* **46**, 7719 (2007).

<sup>11</sup>Zheng Li, Gengfu Chen, Jing Dong, Gang Li, Wanzheng Hu, Dan Wu, Shaokui Su, Ping Zheng, Tao Xiang, Nanlin Wang, and Jianlin Luo, *Phys. Rev. B* **78**, 060504(R) (2008).

<sup>12</sup>Y. Tomioka, S. Ishida, M. Nakajima, T. Ito, H. Kito, A. Iyo, H. Eisaki, and S. Uchida, *Phys. Rev. B* **79**, 132506 (2009).

<sup>13</sup>F. Ronning, N. Kurita, E. D. Bauer, B. L. Scott, T. Park, T. Klimczuk, R. Movshovich, and J. D. Thompson, *J. Phys.: Condens. Matter* **20**, 342203 (2008).

<sup>14</sup>E. D. Bauer, F. Ronning, B. L. Scott, and J. D. Thompson, *Phys. Rev. B* **78**, 172504 (2008).

<sup>15</sup>M. Rotter, M. Tegel, D. Johrendt, I. Schellenberg, W. Hermes, and R. Pöttgen, *Phys. Rev. B* **78**, 020503(R) (2008).

<sup>16</sup>T. Yildirim, *Phys. Rev. Lett.* **101**, 057010 (2008).

<sup>17</sup>Chen Fang, Hong Yao, Wei-Feng Tsai, JiangPing Hu, and Steven A. Kivelson, *Phys. Rev. B* **77**, 224509 (2008).

<sup>18</sup>Kenke Xu, Markus Müller, and Subir Sachdev, *Phys. Rev. B* **78**, 020501(R) (2008).

<sup>19</sup>C. He, Y. Zhang, B. P. Xie, X. F. Wang, L. X. Yang, B. Zhou, F. Chen, M. Arita, K. Shimada, H. Namatame, M. Taniguchi, X. H. Chen, J. P. Hu, and D. L. Feng, *Phys. Rev. Lett.* **105**, 117002 (2010).

<sup>20</sup>L. X. Yang, B. P. Xie, Y. Zhang, C. He, Q. Q. Ge, X. F. Wang, X. H. Chen, M. Arita, J. Jiang, K. Shimada, M. Taniguchi, I. Vobornik, G. Rossi, J. P. Hu, D. H. Lu, Z. X. Shen, Z. Y. Lu, and D. L. Feng, *Phys. Rev. B* **82**, 104519 (2010).

<sup>21</sup>T. Dong, Z. G. Chen, R. H. Yuan, B. F. Hu, B. Cheng, and N. L. Wang, *Phys. Rev. B* **82**, 054522 (2010).

<sup>22</sup>Athena S. Sefat, Michael A. McGuire, Rongying Jin, Brian C. Sales, David Mandrus, Filip Ronning, E. D. Bauer, and Yurij Mozharivskyj, *Phys. Rev. B* **79**, 094508 (2009).

<sup>23</sup>A. J. Drew, C. Niedermayer, P. J. Baker, F. L. Pratt, S. J. Blundell, T. Lancaster, R. H. Liu, G. Wu, X. H. Chen, I. Watanabe, V. K. Malik, A. Dubroka, M. Rössle, K. W. Kim, C. Baines, and C. Bernhard, *Nature Mater.* **8**, 310 (2009).

<sup>24</sup>A. D. Christianson, E. A. Goremychkin, R. Osborn, S. Rosenkranz, M. D. Lumsden, C. D. Malliakas, I. S. Todorov, H. Claus, D. Y. Chung, M. G. Kanatzidis, R. I. Bewley, and T. Guidi, *Nature (London)* **456**, 930 (2008).

<sup>25</sup>L. Ma, J. Zhang, G. F. Chen, and Weiqiang Yu, *Phys. Rev. B* **82**, 180501(R) (2010).

<sup>26</sup>S. Graser, A. F. Kemper, T. A. Maier, H. P. Cheng, P. J. Hirschfeld, and D. J. Scalapino, *Phys. Rev. B* **81**, 214503 (2010).

<sup>27</sup>M. Yi, D. H. Lu, J. G. Analytis, J.-H. Chu, S.-K. Mo, R.-H. He, M. Hashimoto, R. G. Moore, I. I. Mazin, D. J. Singh,



- Z. Hussain, I. R. Fisher, and Z.-X. Shen, *Phys. Rev. B* **80**, 174510 (2009).
- <sup>28</sup>Y. Zhang, J. Wei, H. W. Ou, J. F. Zhao, B. Zhou, F. Chen, M. Xu, C. He, G. Wu, H. Chen, M. Arita, K. Shimada, H. Namatame, M. Taniguchi, X. H. Chen, and D. L. Feng, *Phys. Rev. Lett.* **102**, 127003 (2009).
- <sup>29</sup>L. X. Yang, Y. Zhang, H. W. Ou, J. F. Zhao, D. W. Shen, B. Zhou, J. Wei, F. Chen, M. Xu, C. He, Y. Chen, Z. D. Wang, X. F. Wang, T. Wu, G. Wu, X. H. Chen, M. Arita, K. Shimada, M. Taniguchi, Z. Y. Lu, T. Xiang, and D. L. Feng, *Phys. Rev. Lett.* **102**, 107002 (2009).
- <sup>30</sup>Bo Zhou, Yan Zhang, Le Xian Yang, Min Xu, Cheng He, Fei Chen, Jia-Feng Zhao, Hong-Wei Ou, Jia Wei, Bin-Ping Xie, Tao Wu, Gang Wu, Masashi Arita, Kenya Shimada, Hirofumi Namatame, Masaki Taniguchi, X. H. Chen, and D. L. Feng, *Phys. Rev. B* **81**, 155124 (2010).
- <sup>31</sup>G.-D. Liu, H.-Y. Liu, L. Zhao, W.-T. Zhang, X.-W. Jia, J.-Q. Meng, X.-L. Dong, J. Zhang, G. F. Chen, G.-L. Wang, Y. Zhou, Y. Zhu, X.-Y. Wang, Z.-Y. Xu, C.-T. Chen, and X. J. Zhou, *Phys. Rev. B* **80**, 134519 (2009).
- <sup>32</sup>Y. Zhang, B. Zhou, F. Chen, J. Wei, M. Xu, L. X. Yang, C. Fang, W. F. Tsai, G. H. Cao, Z. A. Xu, M. Arita, H. Hayashi, J. Jiang, H. Iwasawa, C. H. Hong, K. Shimada, H. Namatame, M. Taniguchi, J. P. Hu, and D. L. Feng, e-print [arXiv:0904.4022](https://arxiv.org/abs/0904.4022) (unpublished).
- <sup>33</sup>Y. Zhang, F. Chen, C. He, L. X. Yang, B. P. Xie, Y. L. Xie, X. H. Chen, Minghu Fang, M. Arita, K. Shimada, H. Namatame, M. Taniguchi, J. P. Hu, and D. L. Feng, *Phys. Rev. B* **82**, 165113 (2010).
- <sup>34</sup>Z. G. Chen, G. Xu, W. Z. Hu, X. D. Zhang, P. Zheng, G. F. Chen, J. L. Luo, Z. Fang, and N. L. Wang, *Phys. Rev. B* **80**, 094506 (2009).
- <sup>35</sup>Fei Chen, Bo Zhou, Yan Zhang, Jia Wei, Hong-Wei Ou, Jia-Feng Zhao, Cheng He, Qing-Qin Ge, Masashi Arita, Kenya Shimada, Hirofumi Namatame, Masaki Taniguchi, Zhong-Yi Lu, Jiangping Hu, Xiao-Yu Cui, and D. L. Feng, *Phys. Rev. B* **81**, 014526 (2010).
- <sup>36</sup>W. A. Harrison, *Electronic Structure and the Properties of Solids: The Physics of the Chemical Bond* (Dover, New York, 1989).
- <sup>37</sup>Bo Zhou, L. X. Yang, Fei Chen, Min Xu, Tao Wu, Gang Wu, X. H. Chen, and D. L. Feng, *J. Phys. Chem. Solids*, doi:10.1016/j.jpcs.2010.10.075 (to be published).